



ورقة البيانات الفنية

اسم المنتج: المنيوم ورق

الوصف:

طلاء معدني يستخدم كطلاء نهائي على التجهيزات المعدنية لكي يعطي لون معدني (المنيوم)

المواصفات الفيزيائية:

الكثافة: ٠,٩٦ كغ/ل

اللزوجة (٢٥ درجة مئوية) ٣٠-١٠ c.p

الجفاف الاولي (جفاف دبق): ٢ ساعات بدرجة ٢٥ مئوية

الجفاف النهائي (الجفاف التام): ٤ ساعة بدرجة حرارة ٢٥ مئوية

الوجه التالي بعد: ٢٤ ساعة

المحتوى الصلب: ٣٣%

اللمعان: ٧٠-٤٠ GU @ ٦٠ درجة

اللون: المنيوم معدني

النعومة: ٤٠-١٠ ميكرون

المذيب المناسب: النفط المعدني النقي

التطبيق بواسطة: الفرشاة أو الرول أو فرد الرش

نسبة التخفيف: بدون تخفيف

التعبئة:

عبوات معدنية سعة ٣,٥ ل

عبوات معدنية سعة ٨٧٥ مل

عبوات معدنية سعة ٤٤٠ مل

عبوات معدنية سعة ٢٢٠ مل

التخزين:

يحفظ المنتج في مكان بارد وجاف بعيدا عن اشعة الشمس المباشرة وبعيدا عن متناول الاطفال

Al Jameel International Establishment

For the manufacture of paints and insulating coatings

00963152215226

info@algmeal.com

www.algmeal.com



Technical Data Sheet

Product name: aluminum paper

the description:

Metallic paint used as a final coating on metal fittings to give a metallic color (aluminum)

Physical Specifications:

- **Density:** 0.96kg/l
- **Viscosity** (25°C)10-30 c.p
- **Initial dehydration (sticky dry):** 2 hours at 25°C
- **Final dehydration (complete dehydration):** 4 hours at 25°C
- **Next face after:** 24 hours
- **Solid content:** 33%
- **Gloss :** 40-70 GU @ 60°
- **Color:** metallic aluminum
- **Fineness:** 10-40 microns
- **Suitable solvent:** pure white sprite
- **Application by:** brush, roller or spray applicator
- **Dilution ratio:** no dilution

packing:

3.5 liter metal cans

875ml metal cans

440ml metal cans

220ml metal cans

Storage:

Store the product in a cool, dry place away from direct sunlight and out of reach of children

Al Jameel International Establishment

For the manufacture of paints and insulating coatings

00963152215226

info@algmeal.com

www.algmeal.com