



ورقة البيانات الفنية

اسم المنتج: زيتي أبيض نصف لمعة أول

الوصف:

طلاء ذو اساس زيتي نصف لامع يستخدم كوجه نهائي في الطلاءات المعمارية (اسطح بيتونية او معدنية)

المواصفات الفيزيائية:

الكثافة: ١,٣٠ كغ/ل

اللزوجة (مخفف ٢٥٪ نبط معدني @ ٢٥ درجة مئوية): C.P1٠٠-٩٠

الجفاف الاولي (جفاف دبق): ٤ ساعات بدرجة ٢٥ مئوية

الجفاف النهائي (الجفاف التام): ٢٤ ساعة بدرجة حرارة ٢٥ مئوية

الوجه التالي بعد: ٢٤ ساعة

المحتوى الصلب: ٧٤%

اللمعان: (٥٥-٤٥) GU @ ٦٠ درجة

اللون: ابيض

التعومة: ≥ ٥ ميكرون

المذيب المناسب: النبط المعدني النقي

التطبيق بواسطة: الفرشاة أو الرول أو فرد الرش

نسبة التخفيف: ٢٥٪ نبط معدني نقي

التعبئة:

عبوات معدنية سعة ٣,٥ ل

عبوات معدنية سعة ٨٧٥ مل

التخزين:

يحفظ المنتج في مكان بارد وجاف بعيدا عن اشعة الشمس المباشرة وبعيدا عن متناول الاطفال

Al Jameel International Establishment

For the manufacture of paints and insulating coatings

00963152215226

info@algmeal.com

www.algmeal.com



Technical Data Sheet

Product name: oil white, semi-gloss, first

the description:

Semi-gloss oil-based paint for use as a final finish in architectural coatings (concrete or metal surfaces.)

Physical Specifications:

- **Density:** 1.30 kg/l
- **Viscosity** (dilute 25% pure white sprite @ 25°C): 90-100C.P
- **Initial dehydration (sticky dry):** 4 hours at 25°C
- **Final dryness (total dryness):** 24 hours at 25°C
- **Next face after:** 24 hours
- **Solid content:** 74%
- **Gloss :** (45-55)GU @ 60°
- **color :** white
- **Fineness:** ≤ 5 microns
- **Suitable solvent:** pure white sprite
- **Application by:** brush, roller or spray applicator
- **Dilution ratio:** 25% pure white sprite

packing:

3.5 liter metal cans

875 ml metal cans

Storage:

Store the product in a cool, dry place away from direct sunlight and out of reach of children

Al Jameel International Establishment

For the manufacture of paints and insulating coatings

00963152215226

info@algmeal.com

www.algmeal.com