



ورقة البيانات الفنية

اسم المنتج: زيتي أخضر مت ورق

الوصف:

طلاء ذو اساس زيتي مت يستخدم كوجه نهائي في الطلاءات المعمارية (اسطح بيتونية او معدنية)

المواصفات الفيزيائية:

الكثافة: ١,٢٣ كغ/ل

اللزوجة (مخفف ٢٥٪ نפט معدني @ ٢٥ درجة مئوية) ٦٠-٩٠ c.p

الجفاف الاولي (جفاف دقيق): ٤ ساعات بدرجة ٢٥ مئوية

الجفاف النهائي (الجفاف التام): ٢٤ ساعة بدرجة حرارة ٢٥ مئوية

الوجه التالي بعد: ٢٤ ساعة

المحتوى الصلب: ٦٥,٥٪

اللمعان: ٥٠ @ 60 GU درجة

اللون: أخضر

النعومة: ≥ ٥ ميكرون

المذيب المناسب: النفط المعدني النقي

التطبيق بواسطة: الفرشاة أو الرول أو فرد الرش

نسبة التخفيف: ٢٥٪ نפט معدني نقي

التعبئة:

عبوات معدنية سعة ٣,٥ ل

عبوات معدنية سعة ٨٧٥ مل

عبوات معدنية سعة ٤٤٠ مل

عبوات معدنية سعة ٢٢٠ مل

التخزين:

يحفظ المنتج في مكان بارد وجاف بعيدا عن اشعة الشمس المباشرة وبعيدا عن متناول الاطفال

Al Jameel International Establishment

For the manufacture of paints and insulating coatings

00963152215226

info@algmeal.com

www.algmeal.com



Technical Data Sheet

Product name: Oily green matte paper

the description:

matte oil-based paint for use as a final face in architectural coatings (concrete or metal surfaces).

Physical Specifications:

- **Density:** 1.23kg/l
- **Viscosity** (dilute 25% pure white sprite @ 25°C) 60-90 c.p
- **Initial dehydration (sticky dry):** 4 hours at 25°C
- **Final dryness (total dryness):** 24 hours at 25°C
- **Next face after:** 24 hours
- **Solid content:** 65.5%
- **Gloss :** ≤5 GU @ 60 degrees
- **Color:** green
- **Fineness:** ≤ 5 microns
- **Suitable solvent:** pure white sprite
- **Application by:** brush, roller or spray applicator
- **Dilution ratio:** 25% pure white sprite

packing:

3.5 liter metal cans

875ml metal cans

440ml metal cans

220 ml metal cans

Storage:

Store the product in a cool, dry place away from direct sunlight and out of reach of children

Al Jameel International Establishment

For the manufacture of paints and insulating coatings

00963152215226

info@algmeal.com

www.algmeal.com