



ورقة البيانات الفنية

اسم المنتج: أندركوت زيتي ورق

الوصف:

طلاء ذو اساس زيتي عديم اللمعان (مت) يستخدم كاساس زيتي على الاسطح الاسمنتية او المعادن من اجل تجهيز السطح للطلاء الزيتي النهائي (طبقة اساس نحت الطلاء الزيتي النهائي)

المواصفات الفيزيائية:

الكثافة: ١,٥٣ كغ/ل

اللزوجة (مخفف ٢٥٪ نפט معدني @ ٢٥ درجة مئوية): ٨-٥٣ c.p

الجفاف الاولي (جفاف دبق): ٤٥ دقيقة بدرجة ٢٥ مئوية

الجفاف النهائي (الجفاف التام): ٤ ساعة بدرجة حرارة ٢٥ مئوية

الوجه التالي بعد: ٢٤ ساعة

المحتوى الصلب: ٨٣,٥٪

اللمعان: ٥٥ GU @ ٦٠ درجة

اللون: ابيض

النعومة: ١٥ ≥ ميكرون

المذيب المناسب: النפט المعدني النقي

التطبيق بواسطة: الفرشاة أو الرول أو فرد الرش

نسبة التخفيف: ٢٥٪ نפט معدني نقي

التعبئة:

عبوات معدنية سعة ٣,٥ ل

التخزين:

يحفظ المنتج في مكان بارد وجاف بعيدا عن اشعة الشمس المباشرة وبعيدا عن متناول الاطفال

Al Jameel International Establishment

For the manufacture of paints and insulating coatings

00963152215226

info@algmeal.com

www.algmeal.com



Technical Data Sheet

Product name: Undercoat oily paper

the description:

Matte oil-based paint is used as an oil-based paint on concrete or metal surfaces in order to prepare the surface for the final oil paint (finish oil paint sculpting primer).

Physical Specifications:

- **Density:** 1.53kg/L
- **Viscosity** (diluted 25% pure white sprite @ 25°C): 8-53 c.p
- **Initial dehydration (sticky dry):** 45 minutes at 25°C
- **Final dehydration (complete dehydration):** 4 hours at 25°C
- **Next face after:** 24 hours
- **Solid content:** 83.5%
- **Gloss :** ≤5 GU @ 60°
- **the color** is white
- **Fineness:** ≤ 15 microns
- **Suitable solvent:** pure white sprite
- **Application by:** brush, roller or spray applicator
- **Dilution ratio:** 25% pure white sprite

packing:

3.5 liter metal cans

Storage:

Store the product in a cool, dry place away from direct sunlight and out of reach of children

Al Jameel International Establishment

For the manufacture of paints and insulating coatings

00963152215226

info@algmeal.com

www.algmeal.com