



ورقة البيانات الفنية

اسم المنتج: زيتاى بنى فاتح أول

الوصف:

طلاء ذو اساس زيتي لماع يستخدم كوجه نهائي في الطلاءات المعمارية (اسطح بيتونية او معدنية)

المواصفات الفيزيائية:

الكثافة: ١,١٨ كغ/ل

اللزوجة (مخفف ٢٥٪ نبط معدني @ ٢٥ درجة مئوية) ٩٥-٨٥ c.p

الجفاف الاولي (جفاف دبق): ٤ ساعات بدرجة ٢٥ مئوية

الجفاف النهائي (الجفاف التام): ٢٤ ساعة بدرجة حرارة ٢٥ مئوية

الوجه التالي بعد: ٢٤ ساعة

المحتوى الصلب: ٦٨٪

اللمعان: ٨٥ GU @ ٦٠ درجة

اللون: بنى فاتح

النعومة: ≥ ٥ ميكرون

المذيب المناسب: النبط المعدني النقي

التطبيق بواسطة: الفرشاة أو الرول أو فرد الرش

نسبة التخفيف: ٢٥٪ نبط معدني نقي

التعبئة:

عبوات معدنية سعة ٣,٥ ل

عبوات معدنية سعة ٨٧٥ مل

التخزين:

يحفظ المنتج في مكان بارد وجاف بعيدا عن اشعة الشمس المباشرة وبعيدا عن متناول الاطفال

Al Jameel International Establishment

For the manufacture of paints and insulating coatings

00963152215226

info@algmeal.com

www.algmeal.com



Technical Data Sheet

Product name: oil light brown first

the description:

A glossy oil-based paint for use as a finish in architectural coatings

(concrete or metal surfaces)

Physical Specifications:

- **Density:** 1.18kg/l
- **Viscosity** (diluted 25% pure white sprite @ 25°C): 85-95 c.p
- **Initial dehydration (sticky dry):** 4 hours at 25°C
- **Final dryness (total dryness):** 24 hours at 25°C
- **Next face after:** 24 hours
- **Solid content:** 68%
- **Gloss :** 85 GU @ 60 degrees
- **Color:** light brown
- **Fineness:** ≤ 5 microns
- **Suitable solvent:** pure white sprite
- **Application by:** brush, roller or spray applicator
- **Dilution ratio:** 25% pure white sprite

packing:

3.5 liter metal cans

875 ml metal cans

Storage:

Store the product in a cool, dry place away from direct sunlight and out of reach of children

Al Jameel International Establishment

For the manufacture of paints and insulating coatings

00963152215226

info@algmeal.com

www.algmeal.com